

## Designazioni Bronzi allo Stagno

UNI EN 1652	CEN	AFNOR	DIN	BS	ASTM	ISO
CW450K	CuSn4	CuSn4-p	CuSn4	PB 101	C 51100	CuSn4
CW451K	CuSn5	CuSn5-p	CuSn5	PB 102	C 51000	CuSn5
CW452K	CuSn6	CuSn6-p	CuSn6	PB 103	C 51900	CuSn6
CW453K	CuSn8	CuSn9-p	CuSn8	PB 104	C 52100	CuSn8